Listing of the Claims

This listing of claims is provided for the Examiner's convenience only, no claim amendments have been made by the instant Response:

Listing of Claims:

Claim 1 (Cancelled).

Claim 2 (Previously presented): The thermoplastic molding composition according to Claim 5, wherein the average particle diameter of the compound is 1 nm - $10 \mu m$.

Claim 3 (Previously presented): The thermoplastic molding composition according to Claim 5, wherein the average particle diameter of the compound is 5-500 nm.

Claim 4 (Cancelled).

Claim 5 (Previously presented): A thermoplastic molding composition comprising:

40 to 99 parts by wt. aromatic polycarbonate;

1 to 30 parts by wt. vinyl copolymer;

0.5 to 60 parts by wt. graft polymer; and

0.1 to 30 parts by wt. of an aluminum oxide hydroxide having an average particle diameter of 1 nm - 20 $\mu\text{m}.$

Claim 6 (Cancelled).

Claim 7 (Previously presented): A thermoplastic molding composition comprising:

40 to 99 parts by wt. aromatic polycarbonate;

1 to 30 parts by wt. vinyl copolymer;

0.5 to 60 parts by wt. graft polymer which is a product of copolymerization of 5 to 95 parts by wt. of a mixture of

50 to 95 parts by wt. styrene, α-methylstyrene, styrene substituted on the

nucleus by halogen or alkyl, C_1 - C_8 -alkyl methacrylate, C_1 - C_8 -alkyl acrylate or mixtures thereof, and

5 to 50 parts by wt. acrylonitrile, methacrylonitrile, C₁-C₈-alkyl methacrylate, C₁-C₈-alkyl acrylate, maleic anhydride, C₁-C₄-alkyl or phenyl-N-substituted maleimide or mixtures thereof or 5 to 95 parts by weight of a polymer having a glass transition temperature below -10°C; and 0.1 to 30 parts by wt. of an aluminum oxide hydroxide having an average particle diameter of 1 nm - 20 μm.

Claim 8 (Previously presented): The thermoplastic molding composition of Claim 5 further including at least one additive selected from the group consisting of stabilizers, pigments, mold release agents, flow auxiliaries and antistatics.

Claim 9 (Previously presented): The thermoplastic molding composition of Claim 5 further including at least one additive selected from the group consisting of fillers, reinforcing materials and inorganic compounds.

Claims 10 and 11 (Cancelled).

Claim 12 (Previously presented): In a method of producing a molded article, the improvement comprising including the thermoplastic molding composition of Claim 5.

Claim 13 (Previously presented): The molded article prepared by the method of Claim 12.